



**GARRA S.A.**

POLIG.IND. EITUA N° 14  
48240 BERRIZ (VIZCAYA)  
SPAIN

Tel. 00 34 946824144

Fax.00 34 946824287

e-mail: [garra@garra.es](mailto:garra@garra.es)

[www.garra.es](http://www.garra.es)

**FICHA SUJETACABLE 5/16" GARRA REF.210516**

- **MUELA**

**CALIDAD MATERIAL: FUNDICIÓN MALEABLE**

**ANALISIS QUIMICO TIPO**

C (%)	Si (%)	Mn (%)	P (%)	S (%)
2,40 – 2,70	1,60 – 1,90	0,40 – 0,90	0,06 – 0,08	0,20 – 0,30

- **HORQUILLA M-8**

**CALIDAD MATERIAL: C-15**

**ANALISIS QUIMICO TIPO**

C (%)	Si (%)	Mn (%)	P (%)	S (%)
0,12 – 0,18	0,10 - 0,30	0,25 – 0,60	≤0,05	≤0,05

- **ACABADO: ZINCADO**

